

DUCSIA

Metallic Fine Pearl Decorative Paint












DUCSIA is a decorative paint developed for interior spaces, offering a metallic, fine-pearl, and shimmering appearance.





Thanks to its special pigments, it creates a sparkling look.

It is easy to apply and allows various patterns and textures to be easily created.

It is water-based, environmentally friendly, and harmless to human health.

 CONTENT: <i>Acrylic based - water based</i>	 PACKAGING: <i>1 L ; 2,5 L ; 15 L</i>
 THINNING: <i>Ready to use, do not dilute.</i>	 DRYING TIME: <i>Drying Time Touch dry (at 23°C): 4-6 hours</i> <small>*drying time may be longer at higher relative humidity and lower temperature.</small>
 PRIMER: <i>San Deco Decoprimer</i>	 Fully Dry: <i>24 hours</i>
 APPLICATION TOOL: <i>Brush</i>	 COLORING: <i>Ducsia Color Chart</i>
 NUMBER of COATS: <i>7</i>	 VOC: <i>EU limit value (Directive 2004/42/EC) Category A/I: Decorative effect coatings (water based): 200 g/l (2010) DUCSIA: contains maximum 52 g/l VOC</i>
 STORAGE and SHELF LIFE: <i>Can be stored unopened for 2 years in a cool and dry place, protected from direct sunlight, between +5°C and +35°C.</i>	

CONSUMPTION - Single Coat : *Consumption may vary depending on the type, absorbency, and structure of the surface, as well as the application techniques. For precise consumption, a controlled sample application should be carried out.*

 1 liter covers 7-9 m²
 1 kilogram covers 6-8 m²
Paint consumption for 1 m² is 115-145 ml and 120-150 g.

APPLICATION AREA

It is used with its own primer on interior walls, plaster, exposed concrete, and wooden surfaces after proper surface preparation.

SURFACE PREPARATION

All kinds of dirt, oil, blistered paint, and dust should be removed from the surfaces to be applied.

Surface defects should be repaired with San Deco Acrylic Putty Fine, and then the surface should be primed with San Deco Decoprimer.

SURFACE CONDITIONS

During application and until full drying, the ambient and surface temperature should be between a minimum of +5°C and a maximum of +35°C.

The ambient humidity should be below 75%.

The surface moisture level should be below 10%.

APPLICATION

Ducsia should be applied without dilution, after being thoroughly mixed to a homogeneous consistency, using a brush in a single coat.

Application should be carried out with free and random brush movements to spread the fine particles in the product evenly over the surface.

Once the product is partially dry, the surface should be brushed again to distribute the particles irregularly according to the desired pattern appearance.

Apart from the standard application method, different techniques can be developed if desired.

For more detailed information, product application videos can be viewed.

If more than one batch number is used in the same project, it is recommended to mix the batches equally before application to prevent color tone differences.

Local retouching is not recommended. For retouch-required areas, the entire damaged surface should be re-applied.

HAZARD & PRECAUTIONARY STATEMENTS

- H317: May cause an allergic skin reaction.
P261: Avoid breathing dust/fume/gas/mist/vapors/spray.
P333+P313: If skin irritation or rash occurs: Get medical advice/attention.
P362+P364: Take off contaminated clothing and wash it before reuse.
P280: Wear protective gloves/protective clothing/eye protection/face protection.
P321: Specific treatment (see label).
P272: Contaminated work clothing should not be allowed out of the workplace.

Note: For more information, refer to the product's Safety Data Sheet (SDS).

This technical data sheet has been prepared based on laboratory data under normal conditions. For any details not covered above, please consult technical personnel. Otherwise, errors resulting from insufficient information do not impose responsibility on the manufacturer. The right to make changes to this information is reserved by our company. For detailed information on health, safety, and transport risks and precautions, refer to the Material Safety Data Sheet.

This product is manufactured by Deka Boya Sanayi ve Tic. A.Ş., certified under ISO 9001, ISO 14001, ISO 14064, ISO 45001, and ISO 27001 standards.